

**IN THE CLAIMS:**

Please cancel claims 1-10, and add new claims 11-33 as follows:

1-10 (Cancelled)

11. (New) A field effect transistor comprising:

a SiC surface structure;

a source and a drain formed in said SiC surface structure;

an interface control layer formed adjacent to said SiC surface structure and comprising a Group-III nitride layer, said interface control layer having a film thickness in the range of one molecule-layer to a critical film thickness such that no misfit dislocation occurs with said SiC surface structure;

an insulating structure comprising an insulating layer formed on said interface control layer from a material that is different from said interface control layer and that has a greater band offset with respect to a conduction carrier than said interface control layer; and

a gate electrode formed on said insulating structure.

12. (New) The field effect transistor according to claim 11, wherein said Group-III nitride layer comprises AlN and has a thickness of less than 6 nm.

13. (New) The field effect transistor according to claim 11, wherein said interface control layer comprises a Group-III element including at least one of B, Al, Ga, or In, and N.

14. (New) The field effect transistor according to claim 11, wherein said interface control layer comprises a BAlN layer whose in-plane lattice constant has a mismatch of 0.5% or smaller with respect to the in-plane lattice constant of SiC.

15. (New) The field effect transistor according to claim 11, wherein said insulating layer includes at least one layer selected from the group consisting of a SiO<sub>2</sub> layer, a Si<sub>x</sub>N<sub>y</sub> layer, and an Al<sub>2</sub>O<sub>3</sub> layer.

16. (New) The field effect transistor according to claim 11, wherein said insulating layer is either: an Al<sub>2</sub>O<sub>3</sub> layer that is formed by oxidizing a deposition layer of at least one

material selected from the group consisting of AlN, Al, Al<sub>x</sub>N<sub>y</sub>, AlAs, and AlN<sub>x</sub>As<sub>1-x</sub>, or an Al<sub>2</sub>O<sub>3</sub> layer containing small amounts of at least one of N or As.

17. (New) The field effect transistor according to claim 11, wherein said insulating layer has a multilayered film comprised of a plurality of insulating films.
18. (New) A non-volatile memory element comprising:
  - an SiC surface structure;
  - a floating-gate structure formed on said SiC surface structure, wherein said floating-gate structure includes an interface control layer, a first insulator barrier layer, a floating-gate layer formed of a metal or a semiconductor quantum well, a second insulator barrier layer, and a gate electrode layer, wherein said interface control layer is a Group-III nitride layer formed in contact with said SiC surface structure and having a film thickness in the range of one molecule-layer to a critical film thickness such that no misfit dislocation occurs with said SiC surface structure; and
  - a source and a drain formed on said SiC surface structure adjacent to said floating-gate structure.
19. (New) The nonvolatile memory element according to claim 18, wherein said interface control layer is AlN having a thickness of 6 nm or smaller.
20. (New) The field effect transistor according to claim 18, wherein said first insulator barrier layer has a double-layered film structure on said interface control layer, said double-layered film structure comprising an Al<sub>2</sub>O<sub>3</sub> layer and a SiO<sub>2</sub> layer layered in order.
21. (New) The nonvolatile memory element according to claim 18, wherein said first insulator barrier layer comprises a layer formed from a material that is different from said interface control layer and that has a greater band offset with respect to a conduction carrier than said interface control layer.
22. (New) A method for manufacturing a field effect transistor comprising the steps of:
  - preparing a substrate having a SiC surface structure;
  - forming a source and a drain in said SiC surface structure;

controlling a step structure on the surface of said SiC surface structure and cleaning said surface;

forming an interface control layer adjacent to said SiC surface structure by layer-by-layer growth or step-flow growth, wherein said interface control layer is a Group-III nitride layer and has a thickness of one molecule-layer or greater to a critical film thickness such that no misfit dislocation occurs with said SiC surface structure;

forming an insulating layer on said interface control layer from a material different from that of said interface control layer and having a greater band offset with respect to a conduction carrier than said interface control layer ; and

forming a gate electrode on said insulator layer.

23. (New) The method for manufacturing a field effect transistor according to claim 22, wherein said Group-III nitride layer comprises AlN and has a thickness of 6 nm or smaller.
24. (New) The method for manufacturing a field effect transistor according to claim 11, wherein said SiC surface structure comprises a plane having an offset angle of 15 degrees or smaller with respect to the (0001) plane of 4H-SiC or 6H-SiC, wherein, for controlling the step structure, a step-terrace structure having a height corresponding to the unit period (c-axis lattice constant) of each SiC.
25. (New) A field effect transistor comprising:
  - a SiC surface structure;
  - a source and a drain formed in said SiC surface structure;
  - a single-layer or multilayer insulating structure comprising an interface control layer and an insulating layer, wherein said interface control layer is formed adjacent to said SiC surface structure, contains Al and N, and has a thickness of one molecule-layer or greater, and wherein said insulating layer is formed on said interface control layer from a material that is different from said interface control layer and that has a greater band offset with respect to a conduction carrier than said interface control layer, wherein said insulating layer is either an Al<sub>2</sub>O<sub>3</sub> layer formed by oxidizing a deposition layer of at least one material selected from the group consisting of AlN, Al, Al<sub>x</sub>N<sub>y</sub>, AlAs, and AlN<sub>x</sub>As<sub>1-x</sub>, or an Al<sub>2</sub>O<sub>3</sub> layer that contains a small amount of at least

one of N or As; and

a gate electrode formed on said insulating structure.

26. (New) The field effect transistor according to claim 25, wherein said insulating layer includes a double-layered film structure on said interface control layer, said double-layered film structure comprising an  $\text{Al}_2\text{O}_3$  layer and a  $\text{SiO}_2$  layer in order.
27. (New) A nonvolatile memory element comprising:
  - an SiC surface structure;
  - a floating-gate structure formed on said SiC surface structure including a first insulator barrier layer, a well layer, a second insulator barrier layer, and a gate electrode layer, wherein said first insulator barrier layer is formed in contact with said SiC surface structure and comprises a Group-III nitride epitaxial layer, said well layer is formed of a Group-III nitride epitaxial layer and functions as a floating gate, and said second insulator barrier layer is formed of a Group-III nitride epitaxial layer; and
  - a source and a drain formed in said SiC surface structure adjacent to said floating-gate structure.
28. (New) The nonvolatile memory element according to claim 27, wherein said first insulator barrier layer is a Group-III nitride layer that has a film thickness in the range of one molecule-layer to a critical film thickness such that no misfit dislocation with said SiC surface structure occurs.
29. (New) The nonvolatile memory element according to claim 27, wherein said first insulator barrier layer is a layer comprised of AlN and having a thickness of one molecule-layer or greater to 6 nm or smaller.
30. (New) The nonvolatile memory element according to claim 27, wherein said well layer contains Ga and N.
31. (New) The nonvolatile memory element according to claim 27, wherein said second insulator barrier layer contains Al and N.

32. (New) An electrode to said drain of claim 11 is formed to arbitrary position including front or back side of said SiC surface layer.
33. (New) The field effect transistor according to claim 19, wherein said first insulator barrier layer has a double-layered film structure on said interface control layer, said double-layered film structure comprising an  $\text{Al}_2\text{O}_3$  layer and a  $\text{SiO}_2$  layer layered in order.